

Petrothene® GA501152

Linear Low Density Polyethylene

LyondellBasell Industries

Message:

The Petrothene GA501 series of resins is pelletized liner low density polyethylene selected by customers for film extrusion applications that require excellent drawdown and toughness. These resins have excellent puncture resistance, elongation and heat seal strength. Typical applications include heavy duty shipping sacks, trash can liners, commercial and industrial packaging, as well as food and consumer packaging.

General Information			
Additive	Antiblock (1%)		
	Processing Aid		
	Slip (600 ppm)		
Features	Antiblocking		
	Food Contact Acceptable		
	Good Drawdown		
	Good Heat Seal		
	Good Toughness		
	Puncture Resistant		
	Slip		
Uses	Bags		
	Food Packaging		
	Industrial Applications		
	Liners		
	Packaging		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.918	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested ¹	25	µm	ASTM D882
Secant Modulus			
1% Secant, MD : 25 µm, Blown Film	186	MPa	
1% Secant, TD : 25 µm, Blown Film	193	MPa	ASTM D882
Tensile Strength			
MD : Break, 25 µm, Blown Film	45.5	MPa	

TD : Break, 25 µm,Blown Film	32.4	MPa	
Tensile Elongation			ASTM D882
MD : Break, 25 µm,Blown Film	580	%	
TD : Break, 25 µm,Blown Film	730	%	
Dart Drop Impact (25 µm, Blown Film)	100	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 25 µm, Blown Film	130	g	
TD : 25 µm, Blown Film	330	g	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	107	°C	ASTM D1525
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 25.4 µm, Blown Film)	40		ASTM D2457
Haze (25.4 µm, Blown Film)	20	%	ASTM D1003
Additional Information	Nominal Value		
Blow-up Ratio	2.5:1		
Extrusion	Nominal Value	Unit	
Melt Temperature	204 to 232	°C	
NOTE			

1. Blow-Up Ratio: 2.5:1

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

