

ALTECH® PC A 1000/326 UV

Polycarbonate
ALBIS PLASTIC GmbH

Message:

ALTECH® PC A 1000/326 UV is a Polycarbonate (PC) product. It is available in Asia Pacific, Europe, or North America.
Characteristics include:
REACH Compliant
RoHS Compliant
Antistatic
UV Stabilized

General Information			
Additive	Antistatic		
	UV Stabilizer		
Features	Antistatic		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	15.0	cm³/10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2350	MPa	ISO 527-2
Tensile Stress (Yield)	63.0	MPa	ISO 527-2
Tensile Strain (Yield)	6.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	9.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	130	°C	ISO 75-2/A
Vicat Softening Temperature	144	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature			
Circulation Dryer	100 to 120	°C	
Desiccant Dryer	100 to 120	°C	
Drying Time			
Circulation Dryer	4.0 to 12	hr	
Desiccant Dryer	2.0 to 3.0	hr	
Processing (Melt) Temp	270 to 310	°C	
Mold Temperature	80.0 to 110	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

