Polymer-E EV101

Ethylene Vinyl Acetate Copolymer Asia Polymer Corporation (APC)

Message:

Polymer-E EV101 is an Ethylene Vinyl Acetate Copolymer (EVA) product. It can be processed by extrusion or foam processing and is available in Asia Pacific. Applications of Polymer-E EV101 include consumer goods, foam and sporting goods. Primary characteristic: good processability.

General Information			
Features	Good Processability		
Uses	Foam		
	Footwear		
	Sporting Goods		
Processing Method	Extrusion		
	Foam Processing		
Physical	Nominal Value	Unit	Test Method
Density	0.941	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.1	6		
kg)	1.8	g/10 min	ASTM D1238
Vinyl Acetate Content	18.0	wt%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	35		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	20.6	MPa	ASTM D638
Tensile Elongation (Break)	730	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0	.45		
MPa, Unannealed)	40.0	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

°C

°C

°C

ASTM D746

ASTM D1525

Internal Method

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

< -70.0

65.0

82.0

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

Brittleness Temperature

Melting Temperature

Vicat Softening Temperature

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

