

LEXAN™ XHT5141 resin

Polycarbonate

SABIC Innovative Plastics Europe

Message:

XHT5141 is a high flow, high heat polycarbonate copolymer with a haze onset of 185C. It is available in a range of opaque colors.

General Information			
Features	Copolymer		
	High liquidity		
	Heat resistance, high		
Appearance	Opacity		
	Available colors		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (330°C/2.16 kg)	16	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (330°C/2.16 kg)	15.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.60 - 0.95	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.50	%	ISO 62
Equilibrium, 23°C, 50% RH	0.25	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2600	MPa	ASTM D638
--	2500	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	80.0	MPa	ASTM D638
Yield	80.0	MPa	ISO 527-2/50
Fracture ³	65.0	MPa	ASTM D638
Fracture	65.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	7.5	%	ASTM D638
Yield	7.0	%	ISO 527-2/50
Fracture ⁵	45	%	ASTM D638
Fracture	45	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	2650	MPa	ASTM D790

-- ⁷	2550	MPa	ISO 178
Flexural Stress			
--	120	MPa	ISO 178
Yield, 50.0mm span ⁸	125	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	8.0	kJ/m ²	ISO 179/1eA
23°C	11	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ¹⁰			ISO 179/1eU
-30°C	No Break		ISO 179/1eU
23°C	No Break		ISO 179/1eU
Notched Izod Impact			
-30°C	35	J/m	ASTM D256
23°C	80	J/m	ASTM D256
-30°C ¹¹	8.0	kJ/m ²	ISO 180/1A
23°C ¹²	11	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ¹³			ISO 180/1U
-30°C	No Break		ISO 180/1U
23°C	No Break		ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)	65.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	185	°C	ASTM D648
0.45 MPa, unannealed, 64.0mm span ¹⁴	183	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 3.20mm	174	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹⁵	170	°C	ISO 75-2/Af
Vicat Softening Temperature	190	°C	ASTM D1525, ISO 306/B50, ISO 306/B120 ¹⁶
Ball Pressure Test			IEC 60695-10-2
125°C	Pass		IEC 60695-10-2
165°C	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			
Flow: -40 to 40°C	6.0E-5	cm/cm/°C	ASTM E831
Flow: -40 to 40°C	7.0E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	6.0E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	6.5E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity (25°C)	0.20	W/m/K	ASTM C177
Additional Information	Nominal Value	Unit	Test Method
Metallized Haze Onset	185	°C	Internal method
Injection	Nominal Value	Unit	
Drying Temperature	135	°C	
Drying Time	5.0 - 6.0	hr	

Drying Time, Maximum	48	hr
Suggested Max Moisture	0.020	%
Suggested Shot Size	40 - 60	%
Rear Temperature	300 - 325	°C
Middle Temperature	310 - 335	°C
Front Temperature	320 - 345	°C
Nozzle Temperature	315 - 340	°C
Processing (Melt) Temp	320 - 345	°C
Mold Temperature	110 - 140	°C
Back Pressure	0.300 - 0.700	MPa
Screw Speed	40 - 70	rpm
Vent Depth	0.025 - 0.076	mm

NOTE

1.	5.0 mm/min
2.	Type 1, 50mm/min
3.	Type 1, 50mm/min
4.	Type 1, 50mm/min
5.	Type 1, 50mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*3 sp=62mm
10.	80*10*3 sp=62mm
11.	80*10*3
12.	80*10*3
13.	80*10*3
14.	80*10*4 mm
15.	80*10*4 mm
16.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT