

# Abstron SE32 FR IS15061

Acrylonitrile Butadiene Styrene  
Bhansali Engineering Polymers Limited

Message:

Abstron SE32 FR IS15061 is an acrylonitrile butadiene styrene (ABS) product. It is available in the Asia-Pacific region.  
Features include:  
flame retardant/rated flame  
Flame Retardant

General Information			
Features	Flame retardancy		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.16	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 - 0.60	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, Injection Molded)	100		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield, 3.20 mm, Injection Molded)	37.3	MPa	ASTM D638
Flexural Modulus <sup>2</sup> (6.40 mm, Injection Molded)	1770	MPa	ASTM D790
Flexural Strength <sup>3</sup> (Yield, mm, injection molding)	58.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
23°C, 3.20mm, injection molding	290	J/m	ASTM D256
23°C, 6.40mm, injection molding	250	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load <sup>4</sup> (1.8 MPa, Annealed, 6.40 mm, Injection Molded)	92.0	°C	ASTM D648A
Flammability	Nominal Value	Unit	Test Method
Burning Rate			IS 15061
2.00 mm	< 100	mm/min	IS 15061
3.20 mm	< 100	mm/min	IS 15061
Flame Rating (2.0 mm)	HB		IS 15061
NOTE			
1.	Type 1, 5.0 mm/min		
2.	5.0 mm/min		
3.	5.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

