

TEKNILID PSPPE

Coated Al Foil Film
Tekni-Films, a div of Tekni-Plex

Message:

This data sheet describes TEKNILID PSPPE product
This lid stock is made with a Polyolefin (PO) heat seal (HS) material for Food, Pharmaceutical, and Cosmetic applications requiring a peelable bond to polyethylene (PE), cyclic olefin copolymer (COC), and polypropylene (PP) along with high oxygen and moisture barrier performance.
You peel the foil back to expose the product
This product has excellent puncture and chemical resistance
It is available with custom and standard printing

General Information		
Features	Food Contact Acceptable	
	Good Chemical Resistance	
	Moisture Barrier	
	Oxygen Barrier	
	Puncture Resistant	
Uses	Cosmetics	
	Lids	
	Non-specific Food Applications	
	Pharmaceuticals	
Agency Ratings	FDA Unspecified Rating	
	USP Unspecified Rating	
Forms	Film	
Films	Nominal Value	Unit
Film Thickness ¹	103	µm
Yield	6.57	m ² /kg
Seal Strength		
-- ²	0.44	N/mm
-- ³	0.63	N/mm
-- ⁴	0.63	N/mm
Oxygen Transmission Rate (23°C, 100% RH)	0.0	cm ³ /m ² /24 hr
Water Vapor Transmission Rate (38°C, 90% RH)	0.0	g/m ² /24 hr
NOTE		
1.	Thickness tolerance: ±10%	
2.	To COC @ 350°F, 40psi, 0.5 sec	
3.	To PP @ 350°F, 40psi, 0.5 sec	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

