

Akulon® K125/A

Polyamide 6
DSM Engineering Plastics

Message:

Akulon® K125/A is a Polyamide 6 (Nylon 6) material. It is available in Europe. Primary attribute of Akulon® K125/A: Low Viscosity.

General Information				
Features		Low Viscosity		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.13	--	g/cm ³	ISO 1183
Water Absorption				ISO 62
Saturation, 23°C	9.5	--	%	
Equilibrium, 23°C, 50% RH	2.5	--	%	
Viscosity Number	152	--	cm ³ /g	ISO 307
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	3200	1000	MPa	ISO 527-2
Tensile Stress (Yield)	85.0	45.0	MPa	ISO 527-2
Tensile Strain (Yield)	4.0	25	%	ISO 527-2
Nominal Tensile Strain at Break	20	> 50	%	ISO 527-2
Flexural Modulus	2600	--	MPa	ISO 178
Flexural Stress	100	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	5.0	5.0	kJ/m ²	
23°C	8.0	35	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Melting Temperature ¹	220	--	°C	ISO 11357-3
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0 to 8.0		hr	
Rear Temperature	230 to 235		°C	
Middle Temperature	235 to 250		°C	
Front Temperature	240 to 260		°C	
Nozzle Temperature	240 to 270		°C	

Processing (Melt) Temp	240 to 275	°C
Mold Temperature	50.0 to 80.0	°C
Injection Rate	Moderate-Fast	
Back Pressure	3.00 to 10.0	MPa
Screw Compression Ratio	2.5:1.0	

NOTE

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT