

Durethan® DP AKV 30 FN00 DUS013 000000

Polyamide 66

LANXESS GmbH

Message:

PA 66, 30 % glass fibers, injection molding, halogen free flame retardant

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Additive		Flame Retardant		
Features		Flame Retardant		
		Halogen Free		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.43	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Across Flow : 270°C, 2.00 mm ¹	0.70	--	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.10	--	%	
Flow : 270°C, 2.00 mm ³	0.20	--	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.10	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	10500	6500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	120	75.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.5	5.1	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	9300	5600	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% Strain,23°C	--	120	MPa	
23°C ⁶	190	120	MPa	
Flexural Strain at Flexural Strength ⁷ (23°C)	2.7	4.8	%	ISO 178/A
Residual Moisture Content	0.030 to 0.070		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact Strength (23°C)	10	--	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	45	47	kJ/m ²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				

0.45 MPa, Unannealed	> 250	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	224	--	°C	ISO 75-2/A
Vicat Softening Temperature	240	--	°C	ISO 306/B120
Melting Temperature ⁸	260	--	°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	3.0E+16	4.0E+14	ohms	IEC 60093
Volume Resistivity (23°C)	5.0E+15	5.0E+12	ohms·cm	IEC 60093
Electric Strength (23°C, 1.00 mm)	39	35	kV/mm	IEC 60243-1
Relative Permittivity				IEC 60250
23°C, 100 Hz	3.90	8.70		
23°C, 1 MHz	3.70	4.10		
Dissipation Factor				IEC 60250
23°C, 100 Hz	8.0E-3	0.13		
23°C, 1 MHz	0.012	0.070		
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.400 mm	V-0	--		
0.750 mm	V-0	--		
1.50 mm	V-0	--		
3.00 mm	V-0	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.800 mm	960	--	°C	
1.50 mm	960	--	°C	
3.00 mm	960	--	°C	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.750 mm	725	--	°C	
1.50 mm	725	--	°C	
3.00 mm	725	--	°C	
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	265 to 285		°C	
Mold Temperature	80.0 to 100		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			

3.	60x60x2mm, 80°C MT, 600 bar
4.	60x60x2mm
5.	2.0 mm/min
6.	2.0 mm/min
7.	2 mm/min
8.	10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

