

Geon™ Vinyl Wire & Cable WJAC31L

Flexible Polyvinyl Chloride

PolyOne Corporation

Message:

Geon™ Vinyl Wire & Cable WJAC31L is a flexible PVC product. It can be processed by extrusion coating and is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: wire and cable.

Features include:

ROHS certification

Flame Retardant

General Information			
Features	Flame retardancy		
Uses	Wire and cable applications		
	Communication wire sheath		
Wire Types	CL2		
	CL2R		
	CL3R		
	CMR		
	FPLP		
Agency Ratings	UL 444		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Extrusion coating		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	47		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	20.7	MPa	ASTM D638
Tensile Elongation ² (Break)	280	%	ASTM D638
Aging	Nominal Value	Unit	
Tensile strength retention rate ³ (121°C, 1.91 mm)	100	%	
Elongation retention rate ⁴ (121°C, 1.91 mm)	80	%	
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-28.0	°C	ASTM D746
UL Temperature Rating	90	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257

Flammability	Nominal Value	Unit	Test Method
Oxygen Index (3.18 mm)	34	%	ASTM D2863
Additional Information			
注释:模制厚板(0.075")的典型属性;不能视为技术规格.			
Extrusion	Nominal Value	Unit	
Melt Temperature	177 - 182	°C	
NOTE			
1.	Type 4, 510mm/min		
2.	Type 4, 510mm/min		
3.	336 hours, UL standard		
4.	336 hours, UL standard		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

