

# Hanwha Total PP BJ51W

High Crystallinity Polypropylene  
HANWHA TOTAL PETROCHEMICALS Co., Ltd.

Message:

BJ51W is a polypropylene compound with super weatherability and is ideal for use in outdoor products such as the exteriors of air-conditioning systems. This grade uses a base PP, such as HIPP (High Isotactic Polypropylene), and is manufactured with special processing technology to provide customers with a product of the best quality. This grade possess heightened rigidity, impact-resistance, long-term heat-resistance, as well as protection against thermal discoloration and anti-static property.

General Information			
Additive	Antistatic		
Features	Antistatic		
	Good Processability		
	Good Thermal Stability		
	Good Weather Resistance		
	High Heat Resistance		
	High Impact Resistance		
	High Rigidity		
Uses	Isophthalic		
	Containers		
	Electrical Parts		
	Electrical/Electronic Applications		
	Housings		
	Industrial Applications		
	Outdoor Applications		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	13	g/10 min	ASTM D1238
Molding Shrinkage - Flow (2.00 mm)	1.4 to 1.8	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup>	27.5	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	500	%	ASTM D638
Apparent Bending Modulus	34.3	MPa	ASTM D747
Flexural Modulus <sup>3</sup>	1270	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	105	°C	ASTM D648
Injection	Nominal Value	Unit	
Rear Temperature	180 to 200	°C	
Middle Temperature	190 to 210	°C	
Front Temperature	200 to 220	°C	
Mold Temperature	40.0 to 80.0	°C	
Injection Pressure	58.8 to 98.1	MPa	
Holding Pressure	39.2 to 88.3	MPa	
Screw Speed	30 to 80	rpm	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	5.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

