

4LEX® 10F23300

Polycarbonate
4Plas

Message:

4LEX 10F23300 is a MFI 20 to 22 FR-V2 Polycarbonate

General Information			
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.22	g/cm ³	ISO 1183
Molding Shrinkage - Across Flow	0.50	%	
Water Absorption ¹ (Equilibrium, 23°C, 50% RH)	0.15	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2500	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	60.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	90	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	15	kJ/m ²	ISO 180/1A
23°C	30	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	140	°C	ISO 75-2/B
1.8 MPa, not annealed	135	°C	ISO 75-2/A
Vicat Softening Temperature	148	°C	ISO 306/B
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-2		UL 94
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	3.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Processing (Melt) Temp	260 - 300	°C	
Mold Temperature	80.0 - 100	°C	
Injection Rate	Moderate-Fast		
Holding Pressure	60.0 - 120	MPa	
Screw Speed	200	rpm	

Injection instructions

Feed Throat Temperature: 60 - 80 °C Back Pressure: Low

NOTE

1. 24 Hrs

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

