

MAXAMID™ PA66M40-NC010

Polyamide 66
Pier One Polymers, Inc.

Message:

MAXAMID™ PA66M40 is also available in black, internal and external lubricants, UV stabilized and other modifications.. Further information and details are available upon request.

General Information			
Filler / Reinforcement	Mineral filler, 40% filler by weight		
Additive	Lubricant		
	UV stabilizer		
Features	UV Stabilized		
	Lubrication		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.51	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	96.5	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	3.0	%	ASTM D638
Flexural Modulus (23°C)	6900	MPa	ASTM D790
Flexural Strength (23°C)	152	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	43	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	200	°C	ASTM D648
Peak Melting Temperature	259	°C	ASTM D3418
Injection	Nominal Value	Unit	
Suggested Max Moisture	0.20	%	
Processing (Melt) Temp	290 - 305	°C	
Mold Temperature	65 - 120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

