

3M™ Dyneon™ Fluoroplastic FEP FLEX6305Z

Perfluoroethylene Propylene Copolymer

3M Advanced Materials Division

Message:

3M™ Dyneon™ Fluoroplastic FEP FLEX6305Z is a fully fluorinated copolymer comprising tetrafluoroethylene and hexafluoropropylene and is belonging to the product class FEP. It was developed mainly for heavy gauge wire and cable extrusion and features very high flexibility and stress cracking behavior.

- Special Features
- Excellent dielectric properties
 - High thermal stability
 - Service temperature range up to more than 200 °C
 - Outstanding chemical resistance
 - Wide processing window
 - Excellent flex life properties
 - Extremely low flammability (high LOI)
 - Smooth surface
 - Excellent anti-stick properties
 - Low coefficient of friction
 - Very high weathering and UV stability
 - Very good mechanical properties

General Information	
Features	Low friction coefficient
	High ESCR (Stress Cracking Resistance)
	Copolymer
	Good UV resistance
	Good strength
	Good flexibility
	Good chemical resistance
	Good weather resistance
	Thermal stability, good
	No stickiness
Uses	Films
	Cable sheath
	Wire and cable applications
	Pipe fittings
	Insulating material
	Sheet
Forms	Particle
Processing Method	Film extrusion
	Wire & Cable Extrusion
	Extrusion
	Sheet extrusion molding
	Injection molding

Physical	Nominal Value	Unit	Test Method
Density	2.14	g/cm ³	ISO 12086
Melt Mass-Flow Rate (MFR) (372°C/5.0 kg)	5.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break, 23°C)	30.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	350	%	ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	255	°C	ISO 12086
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (0.250 mm)	110	kV/mm	ASTM D149
Dielectric Constant (23°C)	2.00		ASTM D150
Dissipation Factor	6.6E-4		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	> 95	%	ASTM D2863
Additional Information	Nominal Value		Test Method
MIT Folding Endurance - double folds	300000		ASTM D2176
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	300	°C	
Cylinder Zone 2 Temp.	320	°C	
Cylinder Zone 3 Temp.	340	°C	
Cylinder Zone 4 Temp.	370	°C	
Cylinder Zone 5 Temp.	375	°C	
Die Temperature	370	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT