Manner Flexible PVC X3582C

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

Message:

For the extruded profile and tubing industries, Manner has developed a broad line of products which include low, medium, and high specific gravity materials as well as FDA and NSF recognized compounds. A general purpose transparent offering excellent clarity is also available.

The table below shows some of our most popular compounds, but is not a comprehensive view of the Manner Plastics product portfolio. If you do not see a compound offering the performance your application requires, please contact us. We may already have a custom formulation that meets your needs.

| General Information | | | |
|------------------------------|-------------------|-------|-------------|
| Features | Good Flexibility | | |
| | High Clarity | | |
| | | | |
| Uses | Hose | | |
| | Tubing | | |
| | | | |
| Appearance | Clear/Transparent | | |
| Forms | Pellets | | |
| Processing Method | Extrusion | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.25 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 90 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress (100% Strain) | 11.1 | MPa | ASTM D638 |
| Tensile Strength (Yield) | 21.3 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 380 | % | ASTM D638 |
| Thermal | Nominal Value | Unit | Test Method |
| Brittleness Temperature | -26.0 | °C | ASTM D746 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

