OTECH PVC OW132 - Cable Insulation

Polyvinyl Chloride

OTECH Corporation

Message:

TRAY CABLE INSULATION COMPOUNDS Applications
THHN, THWN, MTW, 60°C OIL

General Information			
Uses	Insulation		
	Wire & Cable Applications		
Physical	Nominal Value	Unit	
Specific Gravity	1.32	g/cm³	
Hardness	Nominal Value	Unit	
Durometer Hardness (10 sec)	92		
Mechanical	Nominal Value	Unit	
Tensile Strength	20.7	МРа	
Tensile Elongation (Break)	280	%	
Additional Information	Nominal Value	Unit	
Limited Oxygen Index	30	%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

