Petrothene® GA501

Linear Low Density Polyethylene LyondellBasell Industries

Message:

The PETROTHENE GA 501 series of resins is pelletized linear low density polyethylene for film extrusion applications that require excellent drawdown and toughness. These resins have excellent puncture resistance, elongation and heat seal strength. Applications include heavy duty shipping sacks, prime liners, commercial and industrial packaging, as well as food and consumer packaging.

General Information			
Features	Food Contact Acceptable		
	Good Drawdown		
	Good Heat Seal		
	Good Toughness		
	Puncture Resistant		
Uses	Bags		
	Food Packaging		
	Industrial Applications		
	Liners		
	Packaging		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.918	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	μm	
Secant Modulus			ASTM D882
1% Secant, MD : 25 μm	186	МРа	
1% Secant, TD : 25 μm	193	MPa	
Tensile Strength			ASTM D882
MD : Break, 25 μm	45.5	MPa	
TD : Break, 25 µm	32.4	MPa	
Tensile Elongation			ASTM D882
MD : Break, 25 μm	580	%	
TD : Break, 25 μm	730	%	
TD : Break, 25 µm Dart Drop Impact (25 µm, Blown Film)	730 100	9 9	ASTM D1709A

MD : 25 μm	130	g	
TD : 25 μm	330	g	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	107	°C	ASTM D1525
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 25.4 µm, Blown Film)	40		ASTM D2457
Haze (25.4 µm, Blown Film)	20	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Melt Temperature	204 to 232	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

