

Sarlink® TPE EE-2260B (PRELIMINARY DATA)

Thermoplastic Elastomer

Teknor Apex Company

Message:

The Sarlink EE-2200 Series is a general purpose thermoplastic elastomer series, available in BLK, designed for automotive exterior extrusion applications. Sarlink EE-2260B is a medium hardness, high density, UV stabilized grade with very good extrudability.

General Information			
Additive	UV stabilizer		
Features	High specific gravity		
	High density		
	Good UV resistance		
	Workability, good		
	Good flexibility		
	Good adhesion		
	Ozone resistance		
	Good toughness		
	Medium hardness		
Uses	Application in Automobile Field		
	Automotive exterior parts		
	Car exterior decoration		
	Rubber substitution		
RoHS Compliance	RoHS compliance		
Appearance	Black		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.50	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ISO 868
Shaw A	63		ISO 868
Shaw A, 15 seconds	60		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
Transverse flow: 100% strain	1.60	MPa	ISO 37
Flow: 100% strain	2.20	MPa	ISO 37
Tensile Stress			ISO 37

Transverse flow: Fracture	9.10	MPa	ISO 37
Flow: Fracture	5.40	MPa	ISO 37
Tensile Elongation			ISO 37
Transverse flow: Fracture	790	%	ISO 37
Flow: Fracture	650	%	ISO 37
Tear Strength - Across Flow	29	kN/m	ISO 34-1
Compression Set			ISO 815
23°C, 22 hr	20	%	ISO 815
70°C, 22 hr	31	%	ISO 815
125°C, 70 hr	77	%	ISO 815
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (200°C, 206 sec ⁻¹)	266	Pa · s	ASTM D3835

Legal statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	193 - 204	°C
Cylinder Zone 2 Temp.	199 - 210	°C
Cylinder Zone 3 Temp.	204 - 216	°C
Cylinder Zone 4 Temp.	210 - 221	°C
Cylinder Zone 5 Temp.	210 - 221	°C
Die Temperature	216 - 227	°C

Extrusion instructions

Screw Speed: 30 to 100 rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT