

EVAL™ F101B

Ethylene Vinyl Alcohol

EVAL Europe nv

Message:

EVAL™F101B is an ethylene-vinyl alcohol (EVOH) product. It is available in Europe.

General Information			
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/2.16 kg	1.6	g/10 min	ISO 1133
210°C/2.16 kg	3.8	g/10 min	ISO 1133
Ethylene Content	32.0	mol%	Internal method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	100		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2700	MPa	ISO 527-2
Tensile Stress (Break)	34.0	MPa	ISO 527-2
Tensile Strain (Break)	15	%	ISO 527-2
Flexural Modulus	3800	MPa	ISO 178
Films	Nominal Value	Unit	Test Method
Oxygen Permeability ¹			ISO 14663-2
20°C, 0% RH	4.0E-3	cm³·mm/m²/atm/24 hr	ISO 14663-2
20°C, 100% RH	0.38	cm³·mm/m²/atm/24 hr	ISO 14663-2
20°C, 35% RH	6.0E-3	cm³·mm/m²/atm/24 hr	ISO 14663-2
20°C, 65% RH	8.0E-3	cm³·mm/m²/atm/24 hr	ISO 14663-2
20°C, 85% RH	0.030	cm³·mm/m²/atm/24 hr	ISO 14663-2
20°C, 90% RH	0.060	cm³·mm/m²/atm/24 hr	ISO 14663-2
Water Vapor Transmission Rate ²	1.6	g·mm/m²/atm/24 hr	ASTM E96
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact Strength	2.9	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	69.0	°C	ISO 11357-2
Vicat Softening Temperature	173	°C	ISO 306
Melting Temperature	183	°C	ISO 11357-3
Peak Crystallization Temperature	161	°C	ISO 11357-3
NOTE			
1.	Annex C		
2.	Procedure E		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

