

Microthene® G MN72700

Low Density Polyethylene

LyondellBasell Industries

Message:

Microthene G polyolefin powders are ground, irregularly-shaped particles for use in a broad range of specialty applications. Microthene G powders combine the unique properties of a polyolefin resin with a small ground particle size.

General Information			
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Powder		
Physical	Nominal Value	Unit	Test Method
Density	0.922	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	24	g/10 min	ASTM D1238
Average Particle Size	16	mesh	
Particle Shape	Irregular		
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore D	56		
Shore D, 15 sec	49		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	8.40	MPa	ASTM D638
Tensile Elongation (Break)	110	%	ASTM D638
Flexural Modulus	342	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-28.3	°C	ASTM D746
Vicat Softening Temperature	86.4	°C	ASTM D1525
Melting Temperature	110	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT