

KIBILAC® PW-997G

Acrylonitrile Styrene Acrylate

CHI MEI CORPORATION

Message:

KIBILAC® PW-997G is an Acrylonitrile Styrene Acrylate (ASA) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Flame Rated

RoHS Compliant

General Information			
Features	Good Colorability		
RoHS Compliance	RoHS Compliant		
Resin ID (ISO 1043)	>ASA<		
Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	4.00	cm ³ /10min	ISO 1133
Molding Shrinkage	0.40 to 0.70	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/50
Yield	45.0	MPa	
Break	35.0	MPa	
Tensile Strain (Break)	50	%	ISO 527-2/50
Flexural Modulus ¹	2000	MPa	ISO 178
Flexural Stress ²	63.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	7.0	kJ/m ²	
23°C	14	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-30°C	6.0	kJ/m ²	
23°C	13	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			ISO 75-2/A
1.8 MPa, Unannealed	83.0	°C	
1.8 MPa, Annealed	100	°C	
Vicat Softening Temperature			
--	109	°C	ISO 306/A50
--	112	°C	ISO 306/A120
--	97.0	°C	ISO 306/B50
--	101	°C	ISO 306/B120

CLTE - Flow	1.0E-4	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT