

WINTEC™ WFW4M

Polypropylene Random Copolymer

Japan Polychem Corporation

Message:

WINTEC™ WFW4M is a Polypropylene Random Copolymer (PP Random Copolymer) product. It can be processed by injection molding and is available in Asia Pacific. Typical application: Film.

General Information			
Uses	Film		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	7.0	g/10 min	ISO 1133
Spiral Flow	46.0	cm	Internal Method
Molding Shrinkage	1.0 to 1.4	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness	90		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1050	MPa	ISO 527-2
Tensile Stress (Yield)	26.0	MPa	ISO 527-2
Nominal Tensile Strain at Break	> 400	%	ISO 527-2
Flexural Modulus	1000	MPa	ISO 178
Flexural Stress	30.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength			ISO 179
0°C	1.0	kJ/m ²	
23°C	6.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	80.0	°C	ISO 75-2/B
Vicat Softening Temperature	125	°C	ISO 306
Optical	Nominal Value	Unit	Test Method
Gardner Gloss	90		ASTM D523
Haze			ISO 14782
1000 μm	25	%	
2000 μm	60	%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

