

Terblend® N NM-19

Acrylonitrile Butadiene Styrene + Nylon

INEOS Styrolution Group GmbH

Message:

Terblend N NM-19 is an ABS/PA blend with excellent impact toughness, good flowability and UV-stabilization.

General Information			
UL YellowCard	E108538-100840284		
Additive	UV Stabilizer		
Features	Good Flow		
	Good Processability		
	Good UV Resistance		
	High Impact Resistance		
Uses	Automotive Applications		
	Automotive Interior Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Multi-Point Data	Specific Volume vs Temperature (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (240°C/10.0 kg)	30.0	cm³/10min	ISO 1133
Molding Shrinkage	0.80	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	1.2	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	103		ISO 2039-2
Ball Indentation Hardness	86.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2000	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	43.0	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	3.5	%	ISO 527-2
Flexural Modulus	1800	MPa	ISO 178
Flexural Stress	62.0	MPa	ISO 178
Films	Nominal Value	Unit	Test Method
Tensile Elongation - MD (Break)	> 50	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	15	kJ/m²	

23°C	65	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Annealed	85.0	°C	ISO 75-2/B
1.8 MPa, Annealed	65.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	160	°C	ISO 306/A50
--	102	°C	ISO 306/B50
CLTE - Flow	1.0E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Relative Permittivity (1 MHz)	2.90		IEC 60250
Dissipation Factor (1 MHz)	0.015		IEC 60250
Injection	Nominal Value	Unit	
Processing (Melt) Temp	240 to 270	°C	
Mold Temperature	40.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

