

DINALON® PA 6.6 IGNÍFUGA

Polyamide 66

Grupo Repol

Message:

DINALON®PA 6.6 IGNU.S. FUGA is a polyamide 66 (nylon 66) product. It can be processed by injection molding and is available in Europe.

Features include:

flame retardant/rated flame

Flame Retardant

General Information			
Additive	Flame retardancy		
Features	Flame retardancy		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm³	ASTM D792
Molding Shrinkage - Flow	2.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	80.0	MPa	ASTM D638
Tensile Elongation (Break)	15	%	ASTM D638
Flexural Modulus	3000	MPa	ASTM D790
Flexural Strength	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact	45	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	200	°C	ASTM D1525
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Additional Information			
Glow Wire, UNE 20-672-83: 650°CVicat Softening Temperature, ASTM D1525: >200°CDTUL, ASTM D648: 100°C			
Injection	Nominal Value	Unit	
Processing (Melt) Temp	275	°C	
Mold Temperature	80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

