

Baytec® MS-051 (HQEE)

Polyurethane (Polyester, MDI)

Covestro - PUR

Message:

Baytec MS-051 is a modified diphenylmethane diisocyanate (MDI)-terminated polyester prepolymer used in the manufacture of high-property solid cast polyurethane elastomers. The excellent resilience and low compression-set properties have enabled this material to be used for low-durometer wheels, printing rolls, and squeegee blades. As with any product, use of Baytec MS-051 prepolymer in a given application must be tested (including field testing, etc.) in advance by the user to determine suitability.

General Information			
Features	Low compressive deformability		
	Elastic		
Uses	Wheels		
	Roller		
Forms	Liquid		
Hardness	Nominal Value	Test Method	
Durometer Hardness (Shore A)	93	ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance (1000 Cycles, 1000 g, H-18 Wheel)	34.0	mg	ASTM D4066
Compression Deflection			ASTM D575
10%	2.90	MPa	ASTM D575
15%	3.96	MPa	ASTM D575
2%	0.621	MPa	ASTM D575
20%	5.03	MPa	ASTM D575
25%	6.21	MPa	ASTM D575
5%	1.69	MPa	ASTM D575
50%	18.4	MPa	ASTM D575
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain	8.07	MPa	ASTM D412
200% strain	9.89	MPa	ASTM D412
300% strain	11.8	MPa	ASTM D412
Tensile Strength (Break)	26.3	MPa	ASTM D412
Tensile Elongation (Break)	650	%	ASTM D412
Tear Strength			
-- ¹	108	kN/m	ASTM D624
Cracking	49	kN/m	ASTM D1938
Compression Set (70°C, 22 hr)	19	%	ASTM D395

Bayshore Resilience	54	%	ASTM D2632
Additional Information			
Appearance: Light amber liquidNCO: 4.9 to 5.2 wt%Flash Point, PMCC: >93°CSpecific Gravity at 80°C: 1.18Specific Gravity at 100°C: 1.17Viscosity at 80°C: 2700 mPa-sViscosity at 700°C: 115 mPa-sNCO/OH Ratio: 1.10Stoichiometry: 90% TheoryPrepolymer Temperature: 100 to 110°CExtender Temperature: 100 to 110°C Mold Temperature: 100 to 110°C Pot Life: 10 to 15 minDemold: 60 min			
NOTE			
1.	C mould		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

