

MAXAMID™ PA666G33HS1L-BK10

Polyamide 66/6 Copolymer

Pier One Polymers, Inc.

Message:

MAXAMID™ PA666G33 is available in natural and black, internal and external lubricants, UV stabilized and other modifications. Further information and details are available upon request.

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Appearance	Black		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	172	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	3.0	%	ASTM D638
Flexural Modulus (23°C)	8970	MPa	ASTM D790
Flexural Strength (23°C)	241	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	215	°C	ASTM D648
Peak Melting Temperature	235	°C	ASTM D3418
Injection	Nominal Value	Unit	
Suggested Max Moisture	< 0.20	%	
Processing (Melt) Temp	290 to 305	°C	
Mold Temperature	65.0 to 120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

