

Starex NH-0700FX

Acrylonitrile Butadiene Styrene

SAMSUNG SDI CO., LTD.

Message:

Starex NH-0700FX is an Acrylonitrile Butadiene Styrene (ABS) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: flame rated.

General Information			
UL YellowCard	E115797-528300		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	3.5	g/10 min	ASTM D1238, ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	111		ASTM D785, ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield ¹	44.0	MPa	ASTM D638
Yield	55.0	MPa	ISO 527-2/50
Flexural Modulus			
-- ²	2400	MPa	ASTM D790
-- ³	2500	MPa	ISO 178
Flexural Strength			
-- ⁴	66.0	MPa	ASTM D790
-- ⁵	75.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C, 3.18 mm	190	J/m	ASTM D256
23°C ⁶	21	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	97.0	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating (0.750 to 3.00 mm)	V-2		UL 94
Injection	Nominal Value	Unit	
Drying Temperature			
--	80.0	°C	
Desiccant Dryer	80.0	°C	
Drying Time			
--	2.0 to 4.0	hr	
Desiccant Dryer	2.0 to 3.0	hr	
Suggested Max Moisture	< 0.050	%	

Rear Temperature	160 to 180	°C
Middle Temperature	190 to 200	°C
Front Temperature	210 to 220	°C
Nozzle Temperature	230	°C
Mold Temperature	40.0 to 80.0	°C
Injection Pressure	49.0 to 147	MPa
Back Pressure	0.490 to 1.96	MPa
Screw Speed	50 to 150	rpm

NOTE

- | | |
|----|-----------------|
| 1. | 50 mm/min |
| 2. | 2.8 mm/min |
| 3. | 2.0 mm/min |
| 4. | 2.8 mm/min |
| 5. | 2.0 mm/min |
| 6. | Thickness: 4 mm |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT