

ELASTOSIL® R plus 4060/50

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, HTV

Molded Parts, Automotive, Plastics and Rubber Processing

Molded Seals, Plastics and Rubber Processing

Membranes, Automotive & Transportation

Molded Parts, Technical, Plastics and Rubber Processing

Molded Parts, Food Contact, Plastics and Rubber Processing

General Information	
Features	Low Compression Set
Uses	Automotive Applications
	Automotive Under the Hood
	Gaskets
	Industrial Applications
	Seals
Processing Method	Compression Molding
	Press Molding

Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	50		DIN 53505
Tensile Strength	8.00	MPa	DIN 53504
Tensile Elongation at Break	500	%	DIN 53504
Compression Set	9.0	%	DIN ISO 815-B
Tear Strength	25.0	kN/m	ASTM D624B
Rebound Resilience	62	%	DIN 53512

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT