

Bynel® 30E671

Ethylene Vinyl Acetate Copolymer
DuPont Packaging & Industrial Polymers

Message:

BYNEL® Series 3000 resins are anhydride-modified ethylene vinyl acetate polymers. They are available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene (PE) resins.

BYNEL 3000 series resins adhere to a wide variety of materials. They are most often used to adhere to PE, ionomers, EVA and polyamide.

General Information	
Features	Good adhesion
Uses	Adhesive
Agency Ratings	FDA 21 CFR 175.105
Forms	Particle
Processing Method	Co-extrusion molding Extrusion

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.932	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.1	g/10 min	ASTM D1238, ISO 1133

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	81.0	°C	ASTM D1525, ISO 306
Peak Melting Temperature	99.0	°C	ASTM D3418, ISO 3146
Freezing Point	87	°C	ASTM D3418

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	135	°C
Cylinder Zone 2 Temp.	185	°C
Cylinder Zone 3 Temp.	210	°C
Cylinder Zone 4 Temp.	235	°C
Cylinder Zone 5 Temp.	235	°C
Adapter Temperature	235	°C
Melt Temperature	< 235	°C
Die Temperature	235	°C

Extrusion instructions

Processing conditions shown are for coextrusion with nylon.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

