

Diakon® LH752

Polymethyl Methacrylate Acrylic
Lucite International Inc.

Message:

Diakon® LH752 is a polymethyl methacrylate-acrylic material. This product is available in Europe and is processed by extrusion or injection molding.
Diakon® The main characteristics of LH752 are:
flame retardant/rated flame
Heat resistance
Typical application areas include:
sheet
Hose

General Information			
Features	Good liquidity		
	Heat resistance, medium		
Uses	Pipe fittings		
	Sheet		
	Profile		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	1.6	g/10 min	ISO 1133
Water Absorption (Equilibrium, 23°C, 50% RH)	0.30	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	95		ISO 2039-2
Ball Indentation Hardness	185	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	83.0	MPa	ISO 527-2
Tensile Strain (Yield)	5.0	%	ISO 527-2
Flexural Modulus	3200	MPa	ISO 178
Flexural Stress	115	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	2.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	20	kJ/m ²	ISO 179/1eU
Notched Izod Impact	1.9	kJ/m ²	ISO 180/1A
Instrumented Dart Impact	0.600	J	ASTM D3763, ISO 6603-2

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	101	°C	ISO 75-2/B
1.8 MPa, not annealed	97.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	110	°C	ISO 306/A
--	104	°C	ISO 306/B
CLTE - Flow	7.1E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Glow Wire Ignition Temperature	650	°C	IEC 60695-2-13
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		ASTM D542, ISO 489
Transmittance	92.0	%	ASTM D1003
Haze	0.40	%	ASTM D1003
Additional Information			

Mold Shrinkage, H 961/30: .4 to .7%.Craze Resistance (isopropanol), Ineos cantilever test: 2000 secs to break.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

