

Prime Polypro™ F337D

Polypropylene Random Copolymer

Prime Polymer Co., Ltd.

Message:

Prime Polypro™ F337D is a Polypropylene Random Copolymer (PP Random Copolymer) product. It can be processed by cast film or film extrusion and is available in Asia Pacific, Europe, or North America. Typical application: Film.

Characteristics include:

Copolymer

Good Sealability

General Information			
Features	Low Temperature Heat Sealability		
	Random Copolymer		
Uses	Cast Film		
	Film		
Processing Method	Cast Film		
	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness	80		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	800	MPa	ISO 527-2
Tensile Stress (Yield)	23.0	MPa	ISO 527-2
Tensile Strain (Break)	> 200	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	13	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	75.0	°C	ISO 75-2/B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

