

Kingfa API-1508

Polypropylene

Kingfa

Message:

Kingfa API-1508 is a polypropylene material, which contains a 15% filler. This product is available in North America or Asia Pacific.

The main features of Kingfa API-1508 are:

flame retardant/rated flame

Antistatic

scratch resistance

odorless/tasteless channel

The typical application field of Kingfa API-1508 is: automotive industry

General Information			
Filler / Reinforcement	Filler, 15% filler by weight		
Additive	Antistatic property		
Features	Antistatic property		
	Scratch resistance		
	The smell is low to none		
Uses	Parts under the hood of a car		
	Car interior equipment		
	Car dashboard		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.00	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow (23°C)	1.2 - 1.4	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	70		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (23°C, Injection Molded)	20.0	MPa	ASTM D638
Tensile Elongation ² (Break, 23°C, Injection Molded)	60	%	ASTM D638
Flexural Modulus ³ (23°C, Injection Molded)	1500	MPa	ASTM D790
Flexural Strength ⁴ (23°C, Injection Molded)	31.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20mm, injection molding	45	J/m	ASTM D256
23°C, 3.20mm, injection molding	400	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.40mm, injection molding	100	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm, injection molding	57.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.20 mm)	HB		UL 94
Additional Information			
Filler Content, ISO3451/1, Method A: 15%			
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	2.0 mm/min		
4.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT