Acrigel® ECL

Polymethyl Methacrylate Acrylic Unigel Plásticos

Message:

Natural PMMA in powder for compounding by extrusion molding. Low flow rate, good thermal resistence and good rate stiffness/impact.

General Information			
Features	Good Impact Resistance		
	Good Stiffness		
	Low Flow		
	Medium Heat Resistance		
Forms	Powder		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	2.3	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	96		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	72.0	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	15	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8			
MPa, Unannealed, 3.20 mm)	98.0	°C	ASTM D648
Vicat Softening Temperature			
	102	°C	ASTM D1525 ¹
	110	°C	ASTM D1525 ²
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		ASTM D542
Transmittance	92.0	%	ASTM D1003
NOTE			
1.	Rate A (50°C/h), Loading 2 (50 N)		
2.	Rate B (120°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

