

# Kynar® 740 Red

Polyvinylidene Fluoride

Arkema

## Message:

KYNAR® 740 RED is a semi-crystalline medium-high molecular weight pelletized polymer of vinylidene fluoride which is pigmented red. It is a versatile engineering plastic with an outstanding balance of physical and chemical properties which qualify it for high performance service in a wide range of applications. It is a thermoplastic fluoropolymer capable of being fabricated in standard processing equipment. The molecular weight and molecular weight distribution have been carefully tailored to supply grades suitable for a variety of processing requirements and end-use applications. KYNAR® 740 RED is appropriate for use in most injection molding applications as well as extrusion of pipes and profiles. The red pigment is registered under the code of federal regulations for use in contact with food.

General Information			
Features	Food Contact Acceptable		
	High Molecular Weight		
	Medium Molecular Weight		
	Semi Crystalline		
Uses	Piping		
	Profiles		
Appearance	Red		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.77 to 1.79	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR)	6.0 to 25	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 23°C)	76 to 80		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 23°C	44.8 to 55.2	MPa	
Break, 23°C	34.5 to 55.2	MPa	
Tensile Elongation (Break, 23°C)	20 to 100	%	ASTM D638
Flexural Modulus (23°C)	1380 to 2310	MPa	ASTM D790
Flexural Strength (23°C)	58.6 to 75.8	MPa	ASTM D790
Compressive Strength (23°C)	68.9 to 103	MPa	ASTM D695
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature	165 to 172	°C	ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity <sup>1</sup> (20°C)	2.0E+14	ohms · cm	ASTM D257

Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (232°C, 100 sec <sup>-1</sup> )	1500 to 2300	Pa·s	ASTM D3835
NOTE			
1.	65% R.H.		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

