

Sarlink® TPV 6155N

Thermoplastic Vulcanizate

Teknor Apex Company

Message:

Sarlink® TPV 6155N is a Thermoplastic Vulcanizate (TPV) material. It is available in Asia Pacific, Europe, Latin America, or North America.

General Information			
Appearance	Opaque		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	0.908	g/cm ³	ASTM D792
--	0.910	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240, ISO 868
Shore A, 5 sec, Extruded	53		
Shore A, 5 sec, Injection Molded	58		
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412, ISO 37
Across Flow : 100% Strain	1.80	MPa	
Flow : 100% Strain	2.40	MPa	
Tensile Strength			ASTM D412, ISO 37
Across Flow : Break	4.39	MPa	
Flow : Break	3.40	MPa	
Tensile Elongation			ASTM D412, ISO 37
Across Flow : Break	610	%	
Flow : Break	340	%	
Tear Strength			
Across Flow	21.0	kN/m	ASTM D624
-- ¹	20	kN/m	ISO 34-1
Compression Set			ASTM D395, ISO 815
23°C, 22 hr	27	%	
70°C, 22 hr	40	%	
125°C, 70 hr	57	%	
Additional Information	Nominal Value	Unit	Test Method
Apparent Shear Viscosity - Capillary @ 206/s			
200°C	215	Pa · s	ISO 11443
200°C	215	Pa · s	ASTM D3835
NOTE			
1.	Method Ba, Angle (Unnicked)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

