

Halene P M103

Polypropylene Homopolymer
Haldia Petrochemicals Ltd.

Message:

M103 is a Polypropylene Homopolymer, produced by the latest generation Spheripol Technology. This homopolymer is primarily suitable for Injection Molding Process. M103 combines easy processability with high Strength.

General Information			
Features	Good Processability		
	High Strength		
	Homopolymer		
Uses	General Purpose		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density ¹	0.900	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, Injection Molded)	32.0	MPa	ASTM D638
Tensile Elongation (Yield, Injection Molded)	7.0	%	ASTM D638
Flexural Modulus (Injection Molded)	1300	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection Molded)	35	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	93.0	°C	ASTM D648
Vicat Softening Temperature	153	°C	ASTM D1525 ²
Injection	Nominal Value	Unit	
Rear Temperature	190 to 250	°C	
Middle Temperature	190 to 250	°C	
Front Temperature	190 to 250	°C	
Nozzle Temperature	190 to 250	°C	
Mold Temperature	40.0 to 50.0	°C	
NOTE			
1.	23°C		
2.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

