

Cleapact TI-300

Styrene Butadiene Block Copolymer

DIC Corporation

Message:

Developed with our unique polymerization technology, Cleapact is a type of styrene copolymer resin that excels in the balance of transparency, shock-resistance and molding capacity. Products in this category have a variety of positive characteristics and meet diverse range of user needs.

General Information			
Features	Food Contact Acceptable		
	High Clarity		
	Shock Resistant		
Uses	Food Packaging		
Appearance	Clear/Transparent		
Physical	Nominal Value	Unit	Test Method
Density	1.09	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	3.0	g/10 min	ISO 1133
Molding Shrinkage	0.30 to 0.70	%	Internal Method
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (L-Scale)	75		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield, Injection Molded	51.0	MPa	
Break, Injection Molded	35.0	MPa	
Tensile Strain (Break, Injection Molded)	15	%	ISO 527-2
Flexural Modulus (Injection Molded)	2500	MPa	ISO 178
Flexural Stress (Injection Molded)	75.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (Injection Molded)	8.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	86.0	°C	ISO 306
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Transmittance (Injection Molded)	89.0	%	JIS K7105
Haze (Injection Molded)	3.0	%	JIS K7105
Injection	Nominal Value	Unit	
Drying Temperature	75.0	°C	

Drying Time	3.0	hr
Extrusion	Nominal Value	Unit
Drying Temperature	75.0	°C
Drying Time	3.0	hr

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

