

KMI KM-P1700 NAT

Polysulfone

KMI Group, Inc.

Message:

KMI KM-P1700 NAT is a polysulfone (PSU) product. It is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

General Information			
Appearance	Natural color		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	9.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	95		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	81.8	MPa	ASTM D638
Tensile Elongation (Break)	8.1	%	ASTM D638
Flexural Modulus	2420	MPa	ASTM D790
Flexural Strength	123	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (23°C)	67	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature	177	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT