

# MARPOL® COPP 35.2.0

Polypropylene Copolymer

Marco Polo International, Inc.

## Message:

MARPOL® COPP 35.2.0 is a Polypropylene Copolymer (PP Copolymer) product. It is available in Asia Pacific, Europe, Latin America, or North America. Primary characteristic: copolymer.

| General Information                       |               |                   |             |
|-------------------------------------------|---------------|-------------------|-------------|
| Features                                  | Copolymer     |                   |             |
| Physical                                  | Nominal Value | Unit              | Test Method |
| Specific Gravity                          | 0.900         | g/cm <sup>3</sup> | ASTM D792   |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 35            | g/10 min          | ASTM D1238  |
| Mechanical                                | Nominal Value | Unit              | Test Method |
| Tensile Strength (Yield)                  | 26.2          | MPa               | ASTM D638   |
| Flexural Modulus - 1% Secant <sup>1</sup> | 1370          | MPa               | ASTM D790A  |
| Impact                                    | Nominal Value | Unit              | Test Method |
| Notched Izod Impact (23°C)                | 110           | J/m               | ASTM D256   |
| NOTE                                      |               |                   |             |
| 1.                                        | 1.3 mm/min    |                   |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

