

ULTEM™ 2110EPR resin

Polyether Imide
SABIC Innovative Plastics

Message:

10% Glass fiber filled, high flow Polyetherimide (Tg 217C) with internal mold release and enhanced electroplatability. ECO Conforming, UL94 V0 and 5VA listing.

General Information	
UL YellowCard	E121562-221094
Filler / Reinforcement	Glass Fiber,10% Filler by Weight
Additive	Mold Release
Features	ECO Compliant
	High Flow
	Platable
Agency Ratings	EU Eco
Processing Method	Injection Molding
Multi-Point Data	Flexural DMA (ASTM D4065)
	Pressure-Volume-Temperature (PVT - Zoller Method)
	Shear DMA (ASTM D4065)
	Specific Heat vs. Temperature (ASTM D3417)
	Tensile Fatigue
	Tensile Stress vs. Strain (ASTM D638)
	Thermal Conductivity vs. Temperature (ASTM E1530)
	Viscosity vs. Shear Rate (ASTM D3835)

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	19	g/10 min	ASTM D1238
Molding Shrinkage			Internal Method
Flow : 3.20 mm	0.70 to 0.90	%	
Across Flow : 3.20 mm	0.60 to 0.80	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	5240	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield	119	MPa	
Break	119	MPa	
Tensile Elongation ³			ASTM D638
Yield	3.0	%	
Break	3.0	%	

Flexural Modulus			ASTM D790
100 mm Span ⁴	5170	MPa	
50.0 mm Span ⁵	490	MPa	
Flexural Strength			ASTM D790
Yield, 50.0 mm Span ⁶	200	MPa	
Break, 100 mm Span ⁷	193	MPa	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	69	J/m	ASTM D256
Unnotched Izod Impact (23°C)	530	J/m	ASTM D4812
Instrumented Dart Impact (23°C, Total Energy)	10.8	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.20 mm	210	°C	
0.45 MPa, Unannealed, 6.40 mm	213	°C	
1.8 MPa, Unannealed, 3.20 mm	205	°C	
1.8 MPa, Unannealed, 6.40 mm	207	°C	
Vicat Softening Temperature	210	°C	ASTM D1525 ⁸
CLTE			ASTM E831
Flow : -40 to 40°C	3.6E-5	cm/cm/°C	
Transverse : -40 to 40°C	8.1E-5	cm/cm/°C	
RTI Elec	105	°C	UL 746
RTI Imp	105	°C	UL 746
RTI Str	105	°C	UL 746
Electrical	Nominal Value		Test Method
Arc Resistance ⁹	PLC 6		ASTM D495
Comparative Tracking Index (CTI)	PLC 4		UL 746
High Amp Arc Ignition (HAI)	PLC 3		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 3		UL 746
Hot-wire Ignition (HWI)	PLC 1		UL 746
Flammability	Nominal Value		Test Method
Flame Rating (0.406 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	4.0 to 6.0	hr	
Drying Time, Maximum	24	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 to 60	%	
Rear Temperature	332 to 399	°C	
Middle Temperature	338 to 399	°C	
Front Temperature	343 to 399	°C	
Nozzle Temperature	343 to 399	°C	

Processing (Melt) Temp	349 to 399	°C
Mold Temperature	135 to 163	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 70	rpm
Vent Depth	0.025 to 0.076	mm

NOTE

1.	5.0 mm/min
2.	Type I, 5.0 mm/min
3.	Type I, 5.0 mm/min
4.	2.6 mm/min
5.	1.3 mm/min
6.	1.3 mm/min
7.	2.6 mm/min
8.	Rate B (120°C/h), Loading 2 (50 N)
9.	Tungsten Electrode

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT