

Daelim Po1y® LD-37

Low Density Polyethylene

DAELIM INDUSTRIAL CO., LTD.

Message:

Daelim Po1y® LD-37 is a Low Density Polyethylene product. It can be processed by injection molding and is available in Asia Pacific. Applications of Daelim Po1y® LD-37 include consumer goods, containers and food contact applications.

Characteristics include:

Good Processability

Low Shrinkage

Warp Resistant

General Information			
Features	Good Processability		
	Low Shrinkage		
	Low Warpage		
Uses	Containers		
	Toys		
Agency Ratings	ASTM D 1248, I, Class A, Cat. 2		
	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.918	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	44		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	12.3	MPa	
Break	11.8	MPa	
Tensile Elongation (Break)	350	%	ASTM D638
Flexural Modulus	132	MPa	ASTM D790
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	200	µm	
Tensile Strength			ASTM D882
MD : Break	18.6	MPa	
TD : Break	20.6	MPa	
Dart Drop Impact	840	g	ASTM D1709

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	85.0	°C	ASTM D1525
Injection	Nominal Value	Unit	
Processing (Melt) Temp	190 to 220	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

