

NuSil MED-6381

Silicone

NuSil Technology

Message:

NuSil Technology's unrestricted materials may be considered for long-term implant applications (greater than 29 days). A silicone gel is an unreinforced, loosely crosslinked network of polymers. Due to the lack of reinforcing filler, gels tend to be low in viscosity in the uncured state, allowing flexibility for various processing techniques. Not only can the crosslink density of the silicone polymers be designed to yield a very firm or soft gel, but the work time and cure profile can also be modified. Accordingly, gels can be used in a variety of applications, including sheeting and encapsulating sensors or electronic devices.

Comments: FIRM RTV GEL

| General Information | | |
|-----------------------------|------------------------------------|-------------------|
| Features | Biocompatible | |
| | Breathable | |
| | Low Viscosity | |
| | Room Temperature Vulcanizing | |
| Uses | Electrical/Electronic Applications | |
| | Medical/Healthcare Applications | |
| Agency Ratings | USP Class VI | |
| Forms | Gel | |
| Processing Method | Encapsulating | |
| Thermoset | Nominal Value | Unit |
| Thermoset Components | | |
| Part A | Mix Ratio by Weight: 97 | |
| Part B | Mix Ratio by Weight: 2.5 | |
| Part C | Mix Ratio by Weight: 0.50 | |
| Additional Information | Nominal Value | Unit |
| Cure System | Condensation | |
| Uncured Properties | Nominal Value | Unit |
| Density | 0.978 | g/cm ³ |
| Viscosity | 10 | Pa · s |
| Curing Time (23°C) | 0.50 | hr |
| Cured Properties | Nominal Value | Unit |
| Shore Hardness (Shore OO) | 75 | |
| Tensile Strength | 0.483 | MPa |
| Tensile Elongation at Break | 130 | % |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

