

SD POLYCA™ SI6011W-F10

Polycarbonate

Sumika Styron Polycarbonate Limited

Message:

SD POLYCA™ 870 series, SI8001H and SI6001W are based on silicone type flame retardants instead of conventional bromine type and phosphonate type flame retardants. SD POLYCA 870 series, SI8001H and SI6001W are environmentally friendly polycarbonate resins and show excellent hydrolysis resistance, thermal stability, heat resistance and molding capability.

General Information			
UL YellowCard	E123529-221582		
Additive	Flame retardancy		
Features	Good Heat Resistance		
	Environmental protection		
	Good formability		
	Hydrolysis resistance		
	Thermal stability, good		
	Flame retardancy		
Uses	Electrical/Electronic Applications		
	Architectural application field		
Part Marking Code	>PC-P10 FR(76)		
Physical	Nominal Value	Unit	Test Method
Density	1.27	g/cm ³	ISO 1183
Molding Shrinkage			ASTM D955
Flow	0.30 - 0.50	%	ASTM D955
Transverse flow	0.40 - 0.60	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.18	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3500	MPa	ISO 527-2
Tensile Strength			
--	71.0	MPa	ASTM D638
--	65.0	MPa	ISO 527-2
Tensile Elongation			
Fracture	5.0	%	ASTM D638
Fracture	6.0	%	ISO 527-2
Flexural Modulus	3900	MPa	ASTM D790, ISO 178
Flexural Strength			
--	108	MPa	ASTM D790
--	103	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength	8.0	kJ/m ²	ISO 179
Notched Izod Impact (23°C)	68	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, not annealed	129	°C	ASTM D648
1.8 MPa, not annealed	128	°C	ISO 75-2/A
Flammability	Nominal Value		Test Method
Flame Rating (1.5 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

