

# Ravago Compounds HM-305W (Comp)

Linear Medium Density Polyethylene

Ravago Manufacturing Americas, LLC

Message:

- Key Features:
- Good moldability
  - Exceptional long term outdoor weatherability (UV15)
  - Balance of toughness and rigidity
  - Excellent low temperature impact
  - Excellent environmental stress crack resistance, ESCR
  - Compounded for uniform additive dispersion
  - Natural as well as standard, custom or special effect colors available
  - Stock colors may be available. See Stock color bulletin
  - UL component recognition listing (E141240)
  - Also available in powder form as HMP-305W

General Information			
Features	Good Moldability		
	Good Toughness		
	Good Weather Resistance		
	High ESCR (Stress Crack Resist.)		
	Low Temperature Impact Resistance		
	Medium Rigidity		
UL File Number	E141240		
Appearance	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Compression Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.934	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (100% Igepal, Compression Molded, F50)	1000	hr	ASTM D1693B
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, Compression Molded)	17.9	MPa	ASTM D638
Tensile Elongation (Break, Compression Molded)	400	%	ASTM D638
Flexural Modulus - Tangent (Compression Molded)	862	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648

0.45 MPa, Unannealed, Compression Molded	64.0	°C
1.8 MPa, Unannealed, Compression Molded	41.0	°C
Flammability	Nominal Value	Test Method
Flame Rating		UL 94
1.52 mm	HB	
3.05 mm	HB	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

