

APEX® 4130

Flexible Polyvinyl Chloride

Teknor Apex Company

Message:

APEX®4130 is a flexible polyvinyl chloride material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is: extrusion.

APEX®The main features of the 4130 are:

ROHS certification

Good UV resistance

daylight resistance

APEX®The typical application fields of 4130 are: wire and cable

General Information			
Features	Good UV resistance		
	Sunlight resistance, 720 hours		
Uses	cord sheath		
Wire Types	SJT		
	SJTW		
	SRDT		
	ST		
	STW		
	SVT		
Agency Ratings	UL QMTT2 .E73402		
RoHS Compliance	RoHS compliance		
Appearance	Opacity		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	83		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	17.9	MPa	ASTM D638
Tensile Elongation (Break)	360	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	75.0	°C	ASTM D794
Brittleness Temperature	-27.0	°C	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	29	%	ASTM D2863
Additional Information			

主要建议温度额定值:80 °C耐日光性UL认证:720小时最大伸长保持率,UL 1581,烘箱老化,7天,113°C:86% 拉伸强度保持率,UL 1581,烘箱老化,7天,113°C: 110 %

Extrusion	Nominal Value	Unit
Melt Temperature	179	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT