# SABIC® LDPE PCG02

#### Low Density Polyethylene

Saudi Basic Industries Corporation (SABIC)

#### Message:

Low density polyethylene for Healthcare

Description

SABIC® LDPE grades for healthcare applications are produced under controlled conditions resulting in high product quality, consistency and a high level of purity.

SABIC® LDPE PCG02 is an additive free grade, typically designed for healthcare packaging and can typically be converted by Blow Fill Seal, Blow Molding and Blown Film to produce monodose ampoules, but also intermediate packaging (bags) for active pharmaceutical ingredients.

Compliance to Regulations

General Information

SABIC® LDPE PCG02 complies with the relevant monographs of the European Pharmacopoeia (EP) and the United States Pharmacopoeia (USPVI). The product mentioned herein may not be used for medical healthcare devices or materials intended for temporary or permanent implementation in the human body.

General Information					
Features	High purity				
	Low density				
	No additive				
Uses	Bags				
	Drug packaging				
	Medical/nursing supplies				
	Medical packaging				
Agency Ratings	EP Unspecified Rating				
	USP Class VI				
Forms	Particle				
Processing Method	Blow film				
	Blow molding				
Physical	Nominal Value	Unit	Test Method		
Density	0.921	g/cm³	ISO 1183/A		
Melt Mass-Flow Rate (MFR) (190°C/2.16					
kg)	1.9	g/10 min	ISO 1133		
Mechanical	Nominal Value	Unit	Test Method		
Coefficient of Friction	> 1.0		ASTM D1894		
Films	Nominal Value	Unit	Test Method		
Tensile Modulus			ISO 527-3		
MD	190	МРа	ISO 527-3		
TD	190	МРа	ISO 527-3		
Tensile Stress			ISO 527-3		

MD: Yield	11.0	MPa	ISO 527-3
TD: Yield	11.0	MPa	ISO 527-3
MD: Fracture	30.0	MPa	ISO 527-3
TD: Fracture	17.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3
MD: Fracture	> 100	%	ISO 527-3
TD: Fracture	> 500	%	ISO 527-3
Elmendorf Tear Strength			ISO 6383-2
MD	70000	N	ISO 6383-2
TD	25000	N	ISO 6383-2
Impact	Nominal Value	Unit	Test Method
Impact Strength	200	J/cm	ASTM D4272
Blocking	20	g	Internal method
Re-blocking	50	g	Internal method
Thermal	Nominal Value	Unit	
1110111101	Norminal value	Offit	Test Method
Vicat Softening Temperature	91.0	°C	ISO 306/A
Vicat Softening Temperature	91.0	°C	ISO 306/A
Vicat Softening Temperature  Melting Temperature (DSC)	91.0 108	°C	ISO 306/A DIN 53765
Vicat Softening Temperature  Melting Temperature (DSC)  Optical	91.0 108 Nominal Value	°C	ISO 306/A DIN 53765 Test Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

