

AMTOPP WT30

Polypropylene
Inteplast Group

Message:

Solid White Industrial
BIAXIALLY ORIENTED POLYPROPYLENE FILM NON HEAT-SEALABLE

General Information			
Uses	Film		
Physical	Nominal Value	Unit	
Dimensional Stability ¹			
Across Flow, 130°C	< 3.0	%	
Flow, 130°C	< 5.0	%	
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	29	µm	
Tensile Strength			ASTM D882
MD : Yield	138	MPa	
TD : Yield	221	MPa	
Tensile Elongation			ASTM D882
MD : Break	140	%	
TD : Break	60	%	
Yield ²	36.6	m²/kg	
Surface Energy			ASTM D2578
-- ³	36	dyne/cm	
-- ⁴	40	dyne/cm	
Optical	Nominal Value	Unit	Test Method
Opacity	62	%	ASTM D589
NOTE			
1.	5 minutes		
2.	Internal Method		
3.	Corona Side if two sided treatment		
4.	High Energy Flame Side		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

