

Spartech Polycom SC1-4090

Acrylonitrile Butadiene Styrene

Spartech Polycom

Message:

Spartech SC1-4091 is a medium viscosity ABS resin for injection molding. It is heat stabilized and lubricated for good processing characteristics, and it exhibits good impact and chemical resistance.

With the benefit of low moisture absorption, ABS can be used in a variety of environments. Being a very versatile product, SC1-4091 can be used for industrial, transportation, sporting goods and electrical/electronic applications.

General Information			
Additive	heat stabilizer		
	Lubricant		
Features	Low hygroscopicity		
	Impact resistance, good		
	Workability, good		
	Good chemical resistance		
	Thermal Stability		
	Thermal stability, good		
	Lubrication		
	General		
	Medium viscosity		
Uses	Electrical/Electronic Applications		
	Industrial application		
	Application in Automobile Field		
	Sporting goods		
	General		
Appearance	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	40.0	MPa	ASTM D638
Flexural Modulus (23°C)	2280	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	210	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	95.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	87.8	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	210 - 240	°C	
Middle Temperature	215 - 245	°C	
Front Temperature	220 - 250	°C	
Nozzle Temperature	218 - 260	°C	
Processing (Melt) Temp	218 - 260	°C	
Mold Temperature	43.3 - 65.6	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

