

# NuSil CV-2566

Silicone

NuSil Technology

Message:

Controlled Volatility (CV) Silicone Materials

Silicone's ability to remain elastic at low temperatures and resistant to breakdown at high temperatures offer excellent utility in extraterrestrial environments where materials are repeatedly exposed to extreme temperatures. NuSil's Controlled Volatility (CV) and Ultra Low Outgassing TM (SCV) silicone products are used by leading space programs to provide the much-needed resilient protection they require against contamination and material degradation.

Benefits of Silicone Materials for Space

Broad Operating Temperature

Compensation for CTE Mismatch

Protection Against Atomic Oxygen

Optically Clear Formulations

Flight Legacy

Comments: Pourable RTV Cure, Primed Lap Shear 500 psi (3.4 MPa)

General Information		
Features	Low to No Outgassing	
Uses	Adhesives	
	Aerospace Applications	
	Electrical/Electronic Applications	
	Sealants	
Agency Ratings	ASTM E 595	
	NASA SP-R-0022A	

Thermal	Nominal Value	Unit
CLTE - Flow	3.3E-4	cm/cm/°C

Thermoset	Nominal Value	Unit
Thermoset Components		
Part A	Mix Ratio by Weight: 100	
Part B	Mix Ratio by Weight: 0.50	

Additional Information	Nominal Value	Unit
Cure System	Alkoxy	

Uncured Properties	Nominal Value	Unit
Color	Red	
Density	1.49	g/cm³
Viscosity	55	Pa · s
Curing Time (23°C)	1.7E+2	hr
Pot Life	180	min

Cured Properties	Nominal Value	Unit
Shore Hardness (Shore A)	55	
Lap Shear Strength <sup>1</sup>	3.45	MPa

Tensile Strength	6.55	MPa
Tensile Elongation at Break	150	%
Tear Strength	7.01	kN/m
Electric Strength	32	kV/mm

NOTE

1.
- Primed with SP-120

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT