Cheng Yu N6GV2

Polyamide 6

Cheng Yu Plastic Company Limited

Message:

Cheng Yu N6GV2 is a Polyamide 6 (Nylon 6) product filled with 20% glass fiber. It is available in Asia Pacific. Characteristics include: Flame Rated Flame Retardant

| General Information | | | |
|---|----------------------------------|-------|-------------|
| Filler / Reinforcement | Glass Fiber,20% Filler by Weight | | |
| Additive | Flame Retardant | | |
| Features | Flame Retardant | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.31 | g/cm³ | ASTM D792 |
| Molding Shrinkage | | | ASTM D955 |
| Flow | 0.40 to 0.60 | % | |
| Across Flow | 1.0 to 1.2 | % | |
| Water Absorption (Saturation) | 1.2 | % | ASTM D570 |
| Hardness | Nominal Value | Unit | Test Method |
| Rockwell Hardness (M-Scale) | 94 | | ASTM D785 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | 145 | МРа | ASTM D638 |
| Flexural Strength | 235 | МРа | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Unnotched Izod Impact (23°C) | 90 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (0.45 MPa, Unannealed) | 228 | °C | ASTM D648 |
| Electrical | Nominal Value | Unit | Test Method |
| Surface Resistivity | 1.0E+17 | ohms | ASTM D257 |
| Dielectric Constant (60 Hz) | 3.50 | | ASTM D150 |
| Flammability | Nominal Value | Unit | Test Method |
| Flame Rating (1.50 mm) | V-0 | | UL 94 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

