

# Delta PSA-2G41

Styrene Maleic Anhydride

Delta Polymers

Message:

Delta PSA-2G41 is a Styrene Maleic Anhydride (SMA) product filled with 20% glass fiber. It is available in North America.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR)	1.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	68.9	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	5520	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256
Flammability	Nominal Value	Unit	Test Method
Burning Rate	< 100	mm/min	ISO 3795

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT